



Datenblatt | Data Sheet

Übersicht | Overview

**KrampeHarex® Melt-Extrakt-Faser | melt extract fibre**

Bezeichnung Name	Länge Length (mm)	Durchmesser Diameter (mm)	Querschnitt Cross section	Form Shape	Material Material	Werkstoff-Nr. Material-No.	Zugfestigkeit Tensile strength (N/mm <sup>2</sup> )
ME 25 – E304	25 ± 10%	0,30 ÷ 1,00	sichelförmig corrugated	—	AISI 304	1.4301	1400 ÷ 1455
ME 25 – E310					AISI 310	1.4845	1400 ÷ 1455
ME 25 – E330					AISI 330	1.4864	1345 ÷ 1425
ME 25 – E430					AISI 430	1.4016	1480 ÷ 1530
ME 25 – E446					AISI 446	1.4762	1425 ÷ 1510

KrampeHarex® GmbH & Co. KG · Pferdekamp 6-8 · 59075 Hamm · Germany  
 Phone +49 (0)23 81 . 977 977 · Fax +49 (0) 23 81 . 977 955 · www.krampeharex.com · info@krampeharex.com

KrampeHarex® CZ spol. s.r.o. · Osvočené 234 · 664 81 Ostrovačice · Czech Republic  
 Phone +42 (0) 549 . 245 064 · Fax +42 (0) 0549 . 245 065 · www.krampeharex.cz · info@krampeharex.cz

KrampeHarex® Fibrin Gesellschaft mbH & Co. KG · Lindengasse 20 · 4040 Linz · Austria  
 Phone +43 (0) 732 731 011 · Fax +43 (0) 732 . 731 011 73 · www.krampefibrin.com · info@krampefibrin.com